1. 1. 1. 100 a 12 5.2.

Planarization Technical Term Dictionary

Edited by
Planarization and CMP Technical Committee, JSPE,Ja

NSF/SRC Engineering Research Center for Environmentally Benign Semiconductor Manufacturing (ERC), U.S.A Preface

Copyrighte/2004 by The Planarization CMP Technical Committee of the Japan Scolety for Precision Committee of the Japan Scolety for Precision Committee of the Japan Scolety for Precision Center for Environmentally Benign Semiconductor Meanufamilities.

All rights of this document are reserved, No part of this book may be reproduced or utilized in any form or by any means, electronic or otherwise, including photocopying, recording or by any information storage and retrieval system, without written permission from the publisher.

Printed in Japan Published in Japan by Global Net Corporation by parnission from The Planartzation CMP Technical committee of the Japan Society for Precision committee at the Japan Society for Precision regineering and the NSP-GRO Engineering Research Center for Environmentally Berign Semiconductor Manufacturing.

Global Net Corporation 3-15-1, Botan, Koto-ku, Tokyo,135-0046 Japan

First published 2004

ISBN4-907847-09-2

This dictionary is based on and includes materials from CMP Technical Term Dictionary in Japanese edition © ISBN4-907847-09-2

edited by
Planarization and CMP Technical Committee,
ISPE, in 2000.

Over the past decade, planarization has proven to be an enabling technology and thus has become mainstream in integrated circuit (IC) manufacturing. Although planarization has its basis in mechanical wafer polishing techniques, it is a polishing process involving chemical phenomena. Since planarization applies to ICs, knowing the basics of IC production is a critical element in understanding the main functions and features of planarization, Understanding the planarization process further requires detailed knowledge regarding the materials, processing equipment, metrology tools and integration schemes involved in implementing this technology. As such, this term dictionary is designed to provide comprehensive explanations relating to devices. It also strives to provide details regarding various unit operations within the IC manufacturing flow. Additionally, post-planarization cleaning terms and definitions are emphasized in this document in order to give the reader a more comprchensive understanding of the entire planarization module.

This is the first edition of the English Dictionary of Planarization Terms published for the general public and will undoubtedly be a very valuable reference book for those working in the planarization and related areas. This publication is the result of fruitful collaboration between the Planarization CMP Technical Committee of the Japan Society for Precision Engineering and the NSF/SRC Engineering Research Center for Environmentally Beniga

(from oils or other organic materials) is easily removed since ice particles cause the organic material to barden and break off. Because of this, ice particles function as oil contamination removal agents. The friction created between the ice and the cleaning objects causes electrostatic charge to build up which can promote contaminant re-adhesion. In order to prevent this from occurring, ions are used to neutralize the charged surface of the wafer. Ice scrubbing is environmentally preferred since it does not involve the use and subsequent disposal of chemicals.

IC pad. IC 1000 pad

De facto standard name of the urethane pad used for CMP process. IC 1000 is a Trademark of Rodel Inc. IC pad was invented by Rodel Inc., currently Rohm and Hazs Electronic Materials CMP Technologies, for inter-layer dielectrics (ILD) CMP under the basis of urethane technology for polishing. The pad is composed of urethane matrix and uniformly distributed micro pores as shown in the cross sectional structure. The pores are spherical in nature and range in diameters from 30-50 µm. The fraction of the pore is about 35% of the pad total volume, but can be changed by manufacturing conditions. The higher the porosity, the lower the pad density. The pore radial size and distribution is also controlled in order to obtain a specific pad hardness, elastic modulus and compressibility, Hardness is measured by using the Shore D hardness test. Typical density of the IC1000 pad is in the range between 0.63 to 0.85 g/cm3 and the corresponding hardness ranges from 52 to 62. The compressibility ranges from 0.5 to 6.0 %. IC 1000 pad can be used either as solo pad or stacked pad. The stacked pad helps to improve both of die size planarity and wafer size planarity at the same time. IC 1000/Suba IV or Suba 400 is a CMP pad stacked with non-woven fabric sub pad and IC 1400 is stacked with foam sub pad.



Cross-sectional view of IC 1000 pad (magnification: ×100)

IC pad